



- PRODUCT MANUFACTURED IN ACCORDANCE WITH CSA A23.4
- STEEL PRODUCTS MANUFACTURED UNDER CSA W47.1 IN ACCORDANCE WITH CSA W59
- MINIMUM CONCRETE STRENGTH AT 28 DAYS: 30 MPA
- MAXIMUM WATER-CEMENT RATIO OF 0.45 & AIR CONTENT OF 5-7%
- EXPOSURE CLASS F2/C4
- HARD STEEL FINISH
- PER MOT SP635 DRAWING 1.1.2

WWW.FRASERWAYPREKAST.COM

(604) 534-2911



MOT TYPE 'A' POLE BASE

SIZE
A

DRAWING #

14730

REV

SHEET

MOT A

1/1